

Technical Data Sheet  
Issued 01.09.09

# DINITROL® 6064

## Hardener

Body Repair

Body Repair

### Characteristics:

DINITROL 6064 is a red hardening paste for all DINITROL putties.  
Based on its red colour, a homogenous mixture of hardener and putty is easy to ensure.

### Method of Use:

Carefully mix the required amount of putty with 2 – 3% of hardening paste.  
Apply to the prepared substrate.

### Technical data:

Product type	Dibenzoyl peroxide 50%
Colours	Red/white
Dosage with UP putty	2% – 3%
Storage	Cool and dry
Storing temperature	< 50°C
Delivery form: Plastic tubes	10 g / 30 g / 50 g / 60 g
Plastic tubes	30 g / 60 g / 200 g

Please refer to the safety data sheet or packaging label for safety instructions.

Die in diesem Merkblatt gemachten Angaben sind das Ergebnis sorgfältiger Untersuchungen. Soweit sie sich auf die Anwendung beziehen, sind sie als Empfehlung zu betrachten, die dem Erfahrungsstand entsprechen. Wegen der Vielseitigkeit der Anwendungs- und Arbeitsweisen können wir jedoch eine Verbindlichkeit nicht übernehmen. Es wird daher ein vertragliches Rechtsverhältnis nicht begründet, und es entstehen aus eventuellen Kaufverträgen keine Nebenverpflichtungen.

All data and recommendations are the result of careful tests by our laboratories. They only can be considered as recommendations which correspond to the level of experience of today. The data are given in good faith. However, in view of the multiplicity of possible application and working methods we are not in a position to assume any responsibility or obligations deriving from the use of our products.

EFTEC Aftermarket GmbH  
Pyrmonter Str. 76  
D-32676 Lügde  
Telephone:  
+49 (0) 52 81 / 9 82 98-0  
Fax:  
+49 (0) 52 81 / 9 82 98-60  
Email:  
service@eftec.de