

Practical Classics May 1993

HOW THEY COMPARED		
RUST KILLERS		POSITION
Rust Remedy	BARE METAL: Surface rusty, small traces of product.	2nd
	PRIMED: Slight corrosion at the edges.	4th
	TOP COATED: Minor stains on the edges and at score mark.	4th
Trustan 23:	BARE METAL: Heavy rust all over.	6th
	PRIMED (using Trustan primer): Rust stains and signs of peeling.	6th
	TOP COATED: Odd rust speckles, corrosion at edges, good resistance at score.	6th
Dinitrol RC 800	BARE METAL: 85% of coat intact.	1st
	PRIMED: Minor rust along edges.	1st
	TOP COATED: Area rust free, with good resistance along score.	1st
Rust Genie	BARE METAL: Heavy rust over most of surface.	5th
	PRIMED: Some peeling and rust staining, poor resistance at score.	5th
	TOP COATED: Peeling along score, minor spots elsewhere.	5th
Jenolite (test 1)	BARE METAL: Surface rust, slight traces of Jenolite.	3rd=
	PRIMED (with Jenolite Double Act): Rust free apart from slight corrosion along score.	2nd=
	TOP COATED: Rust bubbles along score, minor rust stains.	3rd
Jenolite (test 2)	BARE METAL: Surface rust, slight traces of Jenolite.	3rd=
	PRIMED (with Bonda Rust Primer): Slight corrosion along score only.	2nd=
	TOP COATED: Slight rusting along score, light staining on edges.	2nd=
ANTI-RUST PRIMERS		POSITION
Kurust	PRODUCT ONLY (Kurust and Kurust Primer): Uniform rust breakthrough.	9th
	TOP-COATED: Corrosion along bottom edge and at score.	10th
Corroless	PRODUCT ONLY: Some paint lifting along score and top edge.	2nd
	TOP COATED: Paint bubbling along score, stains along bottom edge.	8th
Jenolite Double Act	PRODUCT ONLY: Slight blistering along score and top edge.	3rd=
	TOP COATED: Minor blisters along score.	1st
Eastwood Cold Galvanising	PRODUCT ONLY: One coat as recommended - 50% of coating 'sacrificed'.	10th
	TOP-COATED AREA: Slight rust at edges only.	2nd
Bonda Rust Primer	PRODUCT ONLY: Slight rust along score mark and along top edge.	1st
	TOP COATED: One or two traces of rust, slight staining along edges.	3rd
Finnigans No 1 Rust Beater	PRODUCT ONLY: Rust speckles over much of surface and along score.	7th=
Hammerite	TOP COATED: Rust stains along edges and score.	6th
	PRODUCT ONLY (2 heavy brush coats): Slight deterioration along edges and bubbling along score, remainder rust free.	3rd=
Smoothrite	PRODUCT ONLY (two brush coats): Staining around edges and bubbling along score.	5th
POR 15	PRODUCT ONLY: Blisters along score mark and staining at edges.	6th
	TOP COATED: Surface is corrosion free, apart from bubbling along score.	4th
Control panel:	PRIMED with synthetic cellulose primer: Rust over 40% of surface.	7th=
	TOP COATED: Rust stains along edges and bubbling along score.	7th